

Class Clays

Category Red Earthenware Handbuilding
Source Alfred Claybodies
Name #207 (A.G. Sophomore Hand)
Cone 04
Note For 150 Lbs. RIO=1362g;
Barium=170.25

Recipe

Talc	10
HB 35	20
Om-4	10
RedArt	60

Add

Fine Grog	10
Medium Grog	5
Red Iron Oxide	2%
Barium Carbonate	.25%

Category White Stoneware Throwing
Source Alfred Claybodies
Name #268 (A.C. Sophomore Wheel)
Cone 9-10
Note Replace EPK with Helmer for improved
flashing

Recipe

Hawthorn 35	
mesh	16
EPK	14
FHC	10
Tile-6	20
Tennessee #10	20
NC-4	12
Flint	8

Add

Fine Grog	10
Sand	10

Category Tan/Grey Stoneware Throwing
 Source Alfred Claybodies
 Name #444
 Cone 9-10
 Note Original Calls for Thomas Ball Clay instead of OM-4; Simple, CHEAP body.
 Recipe

OM-4	23.81
Goldart	23.81
Hawthorn 35	38.1
G-200	9.52
Sand	4.76

Category White Stoneware Handbuilding
 Source Alfred Claybodies
 Name #539 (A.C. Jr. Tile)
 Cone 9-10
 Note
 Recipe

Tennessee #10	20
Tile 6	20
EPK	14
Hawthorn 35	16
FHC	10
NC 4	12
Flint	8
Add Fine Grog	10
Medium Grog	10

Category Tan/Grey Stoneware Handbuilding
 Source Alfred Claybodies
 Name #541 (Jr. Sculpture/ Higby Raku)
 Cone Raku
 Note
 Recipe

Hawthorn 35	58.82
OM-4	17.65
Talc	17.65

Sand	5.88
------	------

Category Tan/Grey Stoneware Handbuilding

Source Alfred Claybodies

Name #570 (Linda's Jr. Throwing)

Cone 9-10

Note

Recipe	EPK	16.56
	OM-4	12.42
	Goldart	24.85
	Hawthorn 35	24.85
	Custer	8.28
	Fine Grog	8.28
	Superfine Grog	4.76

Category White Porcelain Throwing

Source Alfred Claybodies

Name #747 (Linda's personal body)

Cone 9-10

Note

Recipe	Grolleg	55.56
	Custer	18.18
	Pyrax	5.05
	Flint	15.15
	Molochite 200	3.03
	Bentonite	3.03

Category Tan/Grey Handbuilding

Source Alfred Claybodies

Name Big (Anton's class)

Cone 04-6

Note Not for C.10!!!

Recipe	Hawthorn 35	25
	OM-4	25
	Talc	25

Fine Grog	8.3
Medium Grog	8.3
Coarse Grog	8.3